JC10 Rec'd PCT/PTO FORM PTO-1390 (REV. 9-2001) U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE ATTORNEY'S DOCKET NUMBE DEC 2 8 201 TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) 37 CFR 1.5 U.S. APPLICATION NO. (If known CONCERNING A FILING UNDER 35 U.S.C. 371 INTERNATIONAL APPLICATION NO. INTERNATIONAL FILING DATE PRIORITY DATE CLAIMED PCT/EP00/05217 June 7, 2000 June 29, 1999 TITLE OF INVENTION METHOD FOR MANUFACTURING FRICTION LININGS APPLICANT(S) FOR DO/EO/US Wolfgang HOGENKAMP and Ernst POLLMANN Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information: 1. This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. 2. This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below. The US has been elected by the expiration of 19 months from the priority date (Article 31). 5. A copy of the International Application as filed (35 U.S.C. 371(c)(2)) is attached hereto (required only if not communicated by the International Bureau). has been communicated by the International Bureau. b. lx l is not required, as the application was filed in the United States Receiving Office (RO/US). 6. An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).  $\mathbf{X}$ is attached hereto. has been previously submitted under 35 U.S.C. 154(d)(4). Amendments to the claims of the International Aplication under PCT Article 19 (35 U.S.C. 371(c)(3)) are attached hereto (required only if not communicated by the International Bureau). have been communicated by the International Bureau. have not been made; however, the time limit for making such amendments has NOT expired. have not been made and will not be made. 8. An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)). 9. 🗓 An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). (unexecuted; executed to follow) 10. An English lanugage translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)). Items 11 to 20 below concern document(s) or information included: An Information Disclosure Statement under 37 CFR 1.97 and 1.98. 11. 12. An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. 13.X A FIRST preliminary amendment. 14. A SECOND or SUBSEQUENT preliminary amendment. 15. A substitute specification. 16. A change of power of attorney and/or address letter. 17. A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825. 18. A second copy of the published international application under 35 U.S.C. 154(d)(4). 19. A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4). 20. Other items or information:

A H A

Ų.

531 Pac'd DITIDT 9 0 DEC 2001					
U.S. APPLICATION NO. PCT/EP00/05217  INTERNATIONAL APPLICATION NO. ATTORNEY'S DOCKET NUMBER  PCT/EP00/05217					
	21. The following fees are submitted:  BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)):				TONS PTO USE ONLY
		492 (a) (1) - (5)): mination fee (37 CFR 1.482)			
nor international se	earch fee (37 CFR	1.445(a)(2)) paid to USPTO prepared by the EPO or JPO	\$1040.00		
USPIO but Interna	International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO\$890.00				
International prelim but international sea	inary examination arch fee (37 CFR 1	fee (37 CFR 1.482) not paid to 1.445(a)(2)) paid to USPTO	to USPTO <b>\$740.00</b>		
but all claims did no	ot satisfy provisions	s of PCT Article 33(1)-(4)	\$710.00		
and all claims satisf	imary examination fied provisions of P	r fee (37 CFR 1.482) paid to University of the U	SPTO \$100.00	<u> </u>	
ENTE	R APPROPRIA	ATE BASIC FEE AMO	UNT =	\$ 890.00	
Surcharge of \$130.0	0 for furnishing the	e oath or declaration later than ty date (37 CFR 1.492(e)).		\$ 130.00	
CLAIMS	NUMBER FILE	D NUMBER EXTRA	RATE	\$	L
Total claims	21 - 20	TOWNED BY THE	x \$18.00	\$ 18.00	
Independent claims	1 -3 =	= 0	x \$84.00	\$ 0	
MULTIPLE DEPENI	DENT CLAIM(S)	(if applicable)AS AMENDED	+ \$280.00	<b>\$</b> 0	
	TOTAL OF ABOVE CALCULATIONS =			\$1038.00	
Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.					
SUBTOTAL = \$1038.00					
Processing fee of \$130.00 for furnishing the English translation later than  20 30 \$ months from the earliest claimed priority date (37 CFR 1.492(f)).				·	
T C	<del></del>	TOTAL NATIO		<b>\$1038.00</b>	
accompanied by an a	enclosed assignme	ent (37 CFR 1.21(h)). The assineet (37 CFR 3.28, 3.31). \$40.0	00 per property +	\$	
TOTAL FEES ENCLOSED = \$1038.00					
				Amount to be refunded	i: °
				charged	l: \$
a. X A check in the amount of \$ 1038.00 to cover the above fees is enclosed.  b. Please charge my Deposit Account No in the amount of \$ to cover the above fees. A duplicate copy of this sheet is enclosed.					
c. X The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 50-1716. A duplicate copy of this sheet is enclosed.					
d. Fees are to be charged to a credit card. WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.					
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137 (a) or (b)) must be filed and granted to restore the application to pending status.					
SEND ALL CORRESPONDENCE TO:					
DILLER, RAMIK & WIGHT					
7345 McWhortor Dlaco, Suita 404					
Annandale, Virginia 22003  (703) 642-5705  Vincent L. Ramik  NAME			<u>ik</u>		
(703) 042-370	5		20,663	3	
Dated: December 28 , 200 1 REGISTRATION NUMBER					

531 Rec'd PCT/F. 28 DEC 2001

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re PCT Patent Application of:

Wolfgang HOGENKAMP

PCT/EP00/05217

International Filing Date: June 7, 2000

Filed in DO/US:

December 28, 2001

METHOD FOR MANUFACTURING FRICTION LININGS

December 28, 2001

**Box PCT** Commissioner for Patents Washington, D.C. 20231

# PRELIMINARY AMENDMENT

Sir:

Contemporaneously with the filing of the above-captioned PCT designated office patent application and prior to examination on the merits thereof, please amend the application as follows:

# IN THE SPECIFICATION:

Page 1, before the title, insert the following heading:

TITLE OF THE INVENTION - -.

Page 1 before pargraph 0001, insert the following heading:

- - BACKGROUND OF THE INVENTION - - .

Page 1, paragraph [0001], rewrite as follows:

[0001] The invention relates to a method of manufacturing friction linings. Page 1, paragaph [0005], cancel in its entirety.

Page 1, between paragraphs [0005] and [0006] insert the following heading:
-- SUMMARY OF THE INVENTION ---

Page 5, between paragraphs [0026] and [0027], insert the following heading:
- - BRIEF DESCRIPTION OF THE DRAWINGS - -.

Page 5, between paragraphs [0031] and [0032], insert the following heading:
- - DESCRIPTION OF THE PREFERRED EMBODIMENTS - -.

Page 10, after the last paragraph ([0052]), please insert the following new paragraph:

[0053] Although a preferred embodiment of the invention has been specifically illustrated and described herein, it is to be understood that minor variations may be made in the apparatus without departing from the spirit and scope of the invention, as defined the appended claims.

# IN THE CLAIMS

Please amend the claims as follows:

3. (Amended) Method according to claim 1, characterized in that the composition of the friction material mixture, in particular the resin content of the friction material mixture, and/or the quantity of the friction material mixture and/or the quantity of a friction material mixture forming the intermediate layer are used as additional manipulated variables.

- 4. (Amended) Method according to claim 1, characterized in that the characteristic value representative of the friction property of the friction linings is obtained from a hysteresis curve of one or a plurality of pressing cycles supplied by measurement of the stamping pressure in dependence on the path travelled by the pressing stamp.
- 9. (Amended) Method according to claim 1, characterized in that the characteristic value representative of the lining property of the friction linings is obtained from a hysteresis curve of one or a plurality of pressing cycles supplied by measurement of the stamping pressure in dependence on the radial pressure acting upon the tool inner wall of the pressing form.
- 13. (Amended) Method according to claim 4, characterized in that the characteristic value is the ascending slope of a predetermined curve section of the hysteresis loop.
- 14. (Amended) Method according to claim 9, characterized in that a predetermined pressure buildup and pressure reduction are controlled in terms of time by means of measurement of the actual pressing time, and measurement of the radial pressure acting upon the tool inner wall during the first pressing cycle or in each pressing cycle.

- 15. (Amended) Method according to claim 4, characterized in that the pressure buildup and the pressure relief of the hysteresis curve are controlled by time control of the stamp pressure such that the ascending slopes of the pressure-buildup curve and the pressure relief curve are almost identical.
- 16. (Amended) Method according to claim 1, characterized in that the energy consumption of the friction material mixture is measured by temperature measurement in the press mold, and the temperature measuring signal controls the press temperature as a manipulated variable.
- 17. (Amended) Method according to claim 1, characterized in that the radiation heat of the friction lining ejected after the pressing process is measured, and the temperature measuring signal controls the press temperature as a manipulated variable.
- 18. (Amended) Method according to claim 1, characterized in that the electrical heating capacity of the press is measured, and the measuring signal controls the press temperature as a manipulated variable.
- 19. (Amended) Method according to claim 1, characterized in that the compressibility, the density, the moduli of elasticity in the three space coordinates, the dimensions of the friction lining or a combination of the aforementioned (lining properties) are used as controlled variable.

Please cancel claim 20 in its entirety.

Please add the following newly drafted claims:

- 21. (New) Method according to claim 9, characterized in that the characteristic value is the ascending slope of a predetermined curve section of the hysteresis loop.
- 22. (New) Method according to claim 9, characterized in that the pressure buildup and the pressure relief of the hysteresis curve are controlled by time control of the stamp pressure such that the ascending slopes of the pressure-buildup curve and the pressure relief curve are almost identical.

# IN THE ABSTRACT:

Line 2, the title, delete in its entirety.

Last line, delete in its entirety ("(Fig. 1)").

## REMARKS

Commensurate with the filing of this application, the Examiner is respectfully requested to introduce this amendment in order that the proper headings are inserted, all multiple dependent claims cancelled and both the government filing fee and examination are based upon the claims of record after the introduction of the present amendment.

The claims now of record for prosecution of the United States national phase are claims 1 through 19 and 21 through 22. The present amendment herewith amends the multiple dependent claims and adds new claims 21 and 22 to cover the cancelled subject matter by way of the dependency thereof from claims 13 and 15.

Upon entry of this amendment, favorable consideration on the merits of the claims is respectfully solicited.

Respectfully submitted

DILLER, RAMIK & WITCHT

Vincent L. Ramik, Attorney Registration No. 20,663

Merrion Square Suite 101 7345 McWhorter Place Annandale, Virginia 22003

(703) 642-5705 - phone (703) 642-2117 - fax

Attachment:

Marked-up Specification and Claims

531 Rec'd PCT/77 28 DEC 2001

New Application - Filed National Phase:

HogenKamp et al. December 28, 2001

PCT/EP00/05217 of 6/29/1999

## MARKED-UP SPECIFICATION

Page 1, line 0001, rewrite as follows:

[0001] The invention relates to a method of manufacturing friction linings [according to the precharaterizing part of claim 1].

# MARKED-UP CLAIMS

- 3. (Amended) Method according to claim 1 [or 2], characterized in that the composition of the friction material mixture, in particular the resin content of the friction material mixture, and/or the quantity of the friction material mixture and/or the quantity of a friction material mixture forming the intermediate layer are used as additional manipulated variables.
- 4. (Amended) Method according to [one of claims 1 to 3] <u>claim 1</u>, characterized in that the characteristic value representative of the friction property of the friction linings is obtained from a hysteresis curve of one or a plurality of pressing cycles supplied by measurement of the stamping pressure in dependence on the path travelled by the pressing stamp.

- 9. (Amended) Method according to [one of claims 1 to 3] <a href="claim 1">claim 1</a>, characterized in that the characteristic value representative of the lining property of the friction linings is obtained from a hysteresis curve of one or a plurality of pressing cycles supplied by measurement of the stamping pressure in dependence on the radial pressure acting upon the tool inner wall of the pressing form.
- 13. (Amended) Method according to claim 4 [or 9], characterized in that the characteristic value is the ascending slope of a predetermined curve section of the hysteresis loop.
- 14. (Amended) Method according to [one of claims 9 to 13] <u>claim 9</u>, characterized in that a predetermined pressure buildup and pressure reduction are controlled in terms of time by means of measurement of the actual pressing time, and measurement of the radial pressure acting upon the tool inner wall during the first pressing cycle or in each pressing cycle.
- 15. (Amended) Method according to claim 4 [or 9], characterized in that the pressure buildup and the pressure relief of the hysteresis curve are controlled by time control of the stamp pressure such that the ascending slopes of the pressure-buildup curve and the pressure relief curve are almost identical.

- 16. (Amended) Method according to [one of claims 1 to 15] <a href="claim 1">claim 1</a>, characterized in that the energy consumption of the friction material mixture is measured by temperature measurement in the press mold, and the temperature measuring signal controls the press temperature as a manipulated variable.
- 17. (Amended) Method according to [one of claims 1 to 15] <u>claim 1</u>, characterized in that the radiation heat of the friction lining ejected after the pressing process is measured, and the temperature measuring signal controls the press temperature as a manipulated variable.
- 18. (Amended) Method according to [one of claims 1 to 15] <u>claim 1</u>, characterized in that the electrical heating capacity of the press is measured, and the measuring signal controls the press temperature as a manipulated variable.
- 19. (Amended) Method according to [one of claims 1 to 18] <u>claim 1</u>, characterized in that the compressibility, the density, the moduli of elasticity in the three space coordinates, the dimensions of the friction lining or a combination of the aforementioned (lining properties) are used as controlled variable.



10/019187 531 Rec'd PCT... 28 DEC 2001

# Method for manufacturing friction linings

**[0001]** The invention relates to a method for manufacturing friction linings according to the precharacterizing part of claim 1.

**[0002]** Compression of the friction linings from a friction material mixture is effected by means of a pressing process comprising at least one pressing cycle performed in a press, wherein a press control unit controls, individually or in combination with each other, a plurality of process parameters as manipulated variables to attain a given lining property of the friction linings. This lining property may e. g. be the compressibility of the friction lining, the density, the moduli of elasticity in the three space coordinates or the dimensions of the friction lining.

**[0003]** Quality deviations of the friction material mixture, wear of tools, temperature changes in the pressing tool as well as tolerances of the press control unit are disturbance variables which may considerably affect the lining property of the friction linings even if all other process parameters remain constant.

**[0004]** It is therefore an object of the invention to provide a method for manufacturing friction linings where malproduction is reduced and the reproducibility of the friction lining properties is increased.

**[0005]** This object is solved with the features of claim 1.

The invention advantageously provides that at least one characteristic value representative for the lining property of the friction linings is measured in a single pressing cycle or in a plurality of pressing cycles and that the process parameters as manipulated variables are controlled in dependence on at least one representative measured characteristic value for the current pressing cycle, for the subsequent pressing cycles and/or subsequent pressing processes. The invention thus aims at measuring the characteristic values during the pressing process and use the thus obtained data for directly controlling the press. Quality deviations of the mixture, wear of tools, temperature change in the pressing tool as well as tolerances of the press control unit can thus be compensated for to a large degree whereby the lining property as a controlled variable can be kept constant. In this manner production variations with regard to the lining properties are minimized and a high reproducibility of the lining

quality is attained. The process according to the invention allows improvement of the automation of the production process, in particular in connection with a process control station for a plurality of presses.

[0007] As manipulated variables the path travelled by the pressing stamp, the stamping pressure, the pressing and venting times and the pressing temperature can be used individually or in combination with each other. These process parameters can be separately measured on the press and controlled by the press control unit. For example, the stamping pressure, the pressing and venting times and the press temperature can be combinedly readjusted within given limits.

**[0008]** Further, the composition of the friction material mixture, in particular the resin content of the friction material mixture, and/or the quantity of friction material mixture and/or the quantity of a friction material mixture forming the intermediate layer can be used as manipulated variables. In this manner quality deviations of the friction material mixture and/or the weight-in quantity of the friction material mixture can be optimized.

**[0009]** The characteristic value representative of the lining property of the friction linings can, according to a first embodiment of the invention, be obtained from a hysteresis loop of one or a plurality of pressing cycles, said hysteresis loop being supplied by measurement of the stamping pressure in dependence on the path travelled by the pressing stamp.

**[0010]** The measurement of the stamping pressure during opening and closing of the pressing tool in dependence on the path travelled by the pressing stamp results in a hysteresis loop whose characteristic values are directly correlated to the compressed friction lining, in particular to the compressibility of the friction lining. For example, the measured value of the area of the hysteresis loop can be directly used as representative characteristic value for press control purposes.

[0011] Alternatively, the representative characteristic value can be obtained from the flow path of the pressing stamp after a given maximum stamping pressure has

been reached. When this given stamping pressure has been reached, the further path travelled by the stamp as from this time up to stillstand of the pressing stamp is measured.

**[0012]** According to a further alternative the maximum value of the path travelled by the stamp can be used as representative characteristic value of the lining property of the friction linings.

**[0013]** The representative characteristic value can also be obtained from the ascending slope of the relief curve section of the hysteresis loop supplied by measurement of the stamping pressure in dependence on the path travelled by the pressing stamp.

**[0014]** According to a second embodiment the characteristic value representative of the lining property of the friction lining can be obtained from a hysteresis curve supplied by measurement of the stamping pressure in dependence on the radial pressure acting upon the tool inner wall of the mold.

**[0015]** The characteristic value can e. g. be the area of this hysteresis curve or the maximum value of the radial pressure acting upon the tool inner wall of the mold.

**[0016]** Further, the representative characteristic value can be the pressure difference of the radial pressure acting upon the tool inner wall of the mold when a given maximum stamping pressure has been reached. This pressure difference correlates well with the compressibility of the friction linings.

**[0017]** Generally, the characteristic value can be the ascending slope value of a predetermined curve section of the hysteresis loop supplied by measurement of the stamping pressure in dependence on the path travelled by the pressing stamp or measurement of the stamping pressure in dependence on the radial pressure acting upon the tool inner wall.

**[0018]** It is possible to control, in terms of time, a predetermined pressure buildup during each pressing cycle by means of measurement of the actual pressing time and measurement of the radial pressure acting upon the tool inner wall.

**[0019]** By measurement of the actual pressing times the aimed pressing times can be exactly adhered to. Form-to-form deviations or press-to-press deviations can be individually compensated for, the same applies to deviations of the pressure buildup and the operating temperature of the press.

**[0020]** The pressure buildup and the pressure relief of the hysteresis curve according to the first and second embodiments can be controlled by time control of the stamping pressure such that the ascending slopes of the pressure buildup curve and the pressure relief curve are almost identical.

**[0021]** By means of temperature measurement the energy consumption of the friction material mixture can be measured, and the temperature measuring signal for controlling the press temperature can be used as manipulated variable.

**[0022]** Alternatively, the radiation heat of the friction lining ejected after the pressing process can be measured, and this temperature measuring signal for controlling the press temperature can be used as manipulated variable.

**[0023]** According to a further alternative, the electrical heating capacity of the press can be measured, wherein this measuring signal controls the press temperature as a manipulated variable.

**[0024]** With regard to the lining properties the compressibility, the density, the moduli of elasticity in the three space coordinates or the dimensions of the friction lining or a combination of the aforementioned friction properties can be used as controlled variable.

**[0025]** The aforementioned method is suited as a method for testing friction lining mixtures. In this manner the reproducibility of the friction material quality can be

checked prior to compression, and the friction material mixture can be corrected, if necessary.

**[0026]** Hereunder embodiments of the invention are described in detail with reference to the drawings in which:

- **[0027]** Fig. 1 shows a schematic representation of the mold in a press,
- [0028] Fig. 2 shows a pressing cycle according to a first embodiment, wherein the stamping pressure is plotted in dependence on the path travelled by the stamp,
- [0029] Fig. 3 shows the correlation between the compressibility of the friction lining and the area of the stamping pressure curve according to Fig. 2,
- [0030] Fig. 4 shows a pressing cycle according to a second embodiment where the stamping pressure is plotted in dependence on the radial pressure, and
- [0031] Fig. 5 shows the correlation between the compressibility of the friction lining in dependence on its flow behaviour as shown in Fig. 4.

**[0032]** Fig. 1 shows a schematic representation of the pressing mold of a press comprising a heating plate 2, a mold or tool 4 and a pressing stamp 8 movable in the tool. The friction material mixture 6 in the pressing mold surrounded by the tool 4 is compressed by the pressing stamp 8 advanced at a predetermined stamping force  $F_{ST}$ , wherein the heating plate 2 and the mold 4 are pressed against each other at a closing force  $F_H$  and a holding-down force  $F_N$ , respectively. On the tool 4 can e. g. be measured the radial pressure exerted by the friction material mixture 6 as the normal force acting upon the tool inner wall, and the temperature of the friction material mixture.

**[0033]** The press control unit can control at least the following process parameters as manipulated variables: path travelled by the stamp  $S_{ST}$ , stamping pressure (stamping force  $F_{ST}$ ), pressing and venting times and press temperature.

**[0034]** Further, these manipulated variables are measured for the purpose of adhering to the aimed values. Moreover, the radial pressure prevailing in the pressing mold is detected during the pressing process.

**[0035]** Further, inter alia, the resin content of the friction material mixture 6 and/or the weight-in quantity of the friction material mixture 6 as the manipulated variables can be changed.

[0036] During the pressing process important process parameters are detected, and the radial pressure occurring in the pressing mold is additionally measured.

**[0037]** The process control is to be effected with a characteristic value representative of the lining property of the friction linings, the characteristic value being measured during a first pressing cycle or in a plurality of pressing cycles of a pressing process. Pressing process means compression of the friction material mixture to form a friction lining, wherein this pressing process may comprise one or a plurality of pressing cycles separated from each other by a venting time. Each pressing cycle comprises a pressure-buildup phase, a holding phase in which a certain stamping pressure is maintained, and a pressure relief phase.

**[0038]** The measured values of the process parameters and the radial pressure determined during a pressing cycle are supplied to the press control unit which can directly change the process parameters used as manipulated variables for the next pressing cycle.

**[0039]** Alternatively, the measured data of a predetermined number of pressing cycles or pressing processes are collected and jointly used, e. g. by averaging, for press controlling purposes. All measured data can further be stored for producing characteristic diagrams related to the characteristic value in order to detect the

influence of various manipulated variables on a characteristic value. These characteristic diagrams can then be used to e. g. simultaneously change a plurality of manipulated variables and optimize the press control.

**[0040]** In the first embodiment it is provided that the characteristic value representative of the lining property of the friction linings is obtained from a hysteresis curve of one or a plurality of pressing cycles supplied by measurement of the stamping pressure in dependence on the path travelled by the pressing stamp.

**[0041]** Fig. 2 shows how the stamping pressure depends on the stamping path  $S_{ST}$ . The stamping pressure is calculated from the stamping force  $F_{ST}$  and the stamping area. The measured values of stamping pressure and stamping path during opening and closing of the pressing tool result in a hysteresis curve. The area SA1 of the hysteresis curve, the flow path SF1, the ascending slope of the relief curve ST1 and the maximum value of the stamping path SW1 can be directly used as characteristic values for press controlling purposes, all the more so since all measured values are available immediately after a pressing process and display a close correlation to the lining properties which are to be kept constant.

**[0042]** Fig. 3 shows e. g. the correlation between the compressibility as a lining property of the friction lining and the area SA1 of the stamping pressure curve shown in Fig. 2. The correlation coefficient amounts to 0.7 such that the area SA1 is a suitable representative characteristic value for controlling the compressibility. In this manner the press can be controlled in terms of pressure buildup and pressure relief, pressing and venting times and press temperature such that a high reproducibility of the lining properties is attained.

**[0043]** According to a second embodiment it is provided that the characteristic value representative of the lining property of the friction linings is obtained from a hysteresis curve of one or a plurality of pressing cycles supplied by measurement of the stamping pressure in dependence on the radial pressure acting upon the tool inner wall of the pressing mold.

[0044] Fig. 4 shows the march of pressure in a pressing cycle during opening and subsequent closing of the pressing tool, wherein the stamping pressure is plotted in dependence on the radial pressure acting upon the tool inner wall. This again results in a hysteresis curve whose area is designated by MA1. As can be seen from the diagram, the stamping pressure is built up to a value of just above 20 MPa and then kept constant for a given period of time. During this time the radial pressure nevertheless increases up to a maximum value MP1. The pressure difference at constant stamping pressure is measured, with this measured value also being characteristic of the flow behaviour of the friction material mixture.

[0045] In Fig. 5 the compressibility of the friction lining is plotted in dependence on the pressure difference MF1. It can be seen from the diagram that the measurement of the pressure difference MF1 of the radial pressure displays a satisfactory correlation to the compressibility of the friction lining. The correlation coefficient of the test series shown in Fig. 5 amounts to 0.6. Thus the pressure difference MF1 is also a suitable representative characteristic value.

[0046] The radial pressure acting upon the tool inner wall results from the viscoelastic properties of the friction material mixture. The measurement of the radial pressure furnishes information on the flowability and the cross-linkage pattern of the compressed friction material mixture. These measurements allow conclusions to be drawn with regard to the resin content, the type of resin used, the homogeneity and the moisture degree of the friction material mixture such that a mixture control can be performed. When the radial pressure deviates from a given aimed value, the press control unit may e. g. change the venting phases between two pressing cycles of a pressing process. These venting phases are provided between at least two pressing cycles in the case of multi-stage pressing.

**[0047]** By suitable arrangement of temperature sensors in the mold the energy consumption of the pressed part can be detected more accurately, and the measured values can be used for more precise heating control. Alternatively, the radiation heat of the friction lining ejected from the pressing mold can be measured, wherein the temperature value and the temperature distribution are a measure for the correct heat

transmission in the friction material mixture. These measured values, too, are suitable for carrying out a precise heating control.

[0048] The dependence of the controlled variable on the representative characteristic value, as exemplary shown in Figs. 3 and 5, is stored in the press control unit as is the dependence of the representative characteristic value on one of the manipulated variables. If therefore a deviation with regard to the lining property as a controlled variable is detected, the press control unit can perform a control of the manipulated variables with the aid of algorithms which reflect the dependence of the representative characteristic value on the manipulated variables such that high reproducibility of the friction property can be obtained.

[0049] Of course, a plurality of manipulated variables can be simultaneously changed to lead the representative characteristic value to a desired value. In this case multi-dimensional characteristic diagrams are stored in the press control unit, the characteristic diagrams including the dependence of the representative characteristic value on a plurality of manipulated variables thus allowing optimization of the pressing process. For the manipulated variables respective given adjustment spectra are specified such that the press control unit can optimize the pressing process by simultaneously controlling a plurality of manipulated variables without selecting any extreme values within the adjustment spectrum of the manipulated variables.

**[0050]** Finally, it is also possible to permanently renew, in a learning cycle, the characteristic diagrams reflecting the dependence of the representative characteristic values on the manipulated variables by storing the measured values detected during the pressing process using a certain tool and a certain friction material mixture.

[0051] The characteristic values SA1, SF1, SW1, ST1 and MA1, MF1 and MP1, respectively, shown in Figs. 2 and 4, relate to a first pressing cycle. These characteristic values of a first pressing cycle can be used individually or in combination with each other for press controlling purposes. It is however also possible to combine the characteristic values SA1 to SAn, SF1 to SFn, SW1 to SWn, MA1 to MAn, MF1 to MFn, and MP1 to MPn of a plurality of pressing cycles in order to control the pressing

process. Preferably, the characteristic values obtained during each pressing cycle are directly used for correcting the manipulated variables used in the previous pressing cycle.

**[0052]** The method allows operation of a press within the range of its capacity, reduction of the pressing times, reduction of the reject rate and simultaneous increase of the lining quality. An essential aspect is that variations in the friction lining mixture can be compensated for by the proposed process control. The method further allows a plurality of presses to be operated with the aid of a process control station.

#### **CLAIMS**

### What is claimed is:

- Method for manufacturing friction linings with or without intermediate layer by compressing the friction material mixture in a mold of a press during a pressing process comprising at least one pressing cycle,
  - wherein a press control unit controls a plurality of manipulated variables individually or in combination with each other in order to attain a given lining property (controlled variable) of the friction linings,

characterized in that

at least one characteristic value representative of the lining property of the friction linings is measured during a first pressing cycle or a plurality of pressing cycles, and the manipulated variables are controlled in dependence on the at least one measured characteristic value of the current pressing cycle, the subsequent pressing cycles and/or the subsequent pressing processes.

- Method according to claim 1, characterized in that the path travelled by the
  pressing stamp, the stamping pressure, the pressing and venting times and the
  press temperature are used, individually or in combination with each other, as
  manipulated variables.
- 3. Method according to claim 1 or 2, characterized in that the composition of the friction material mixture, in particular the resin content of the friction material mixture, and/or the quantity of the friction material mixture and/or the quantity of a friction material mixture forming the intermediate layer are used as additional manipulated variables.
- 4. Method according to one of claims 1 to 3, characterized in that the characteristic value representative of the friction property of the friction linings is obtained from a hysteresis curve of one or a plurality of pressing cycles supplied by measurement of the stamping pressure in dependence on the path travelled by the pressing stamp.

- 5. Method according to claim 4, characterized in that the characteristic value is the area (SA1, ..., SAn) of the hysteresis curve.
- 6. Method according to claim 4, characterized in that the characteristic value is the flow path of the pressing stamp (SF1, ..., SFn) after a given maximum stamping pressure has been reached.
- 7. Method according to claim 4, characterized in that the characteristic value is the maximum value (SW1, ..., SWn) of the stamp path.
- 8. Method according to claim 4, characterized in that the characteristic value is the ascending slope of the relief curve section (ST1, ..., STn).
- 9. Method according to one of claims 1 to 3, characterized in that the characteristic value representative of the lining property of the friction linings is obtained from a hysteresis curve of one or a plurality of pressing cycles supplied by measurement of the stamping pressure in dependence on the radial pressure acting upon the tool inner wall of the pressing form.
- 10. Method according to claim 9, characterized in that the characteristic value is the area (MA1, ..., MAn) of the hysteresis curve.
- 11. Method according to claim 9, characterized in that the characteristic value is the maximum value (MP1, ..., MPn) of the radial pressure acting upon the tool inner wall of the mold.
- 12. Method according to claim 9, characterized in that the characteristic value is the pressure difference (MF1, ..., MFn) of the radial pressure acting upon the tool inner wall of the mold after a given maximum stamping pressure has been reached.
- 13. Method according to claim 4 or 9, characterized in that the characteristic value is the ascending slope of a predetermined curve section of the hysteresis loop.

- 14. Method according to one of claims 9 to 13, characterized in that a predetermined pressure buildup and pressure reduction are controlled in terms of time by means of measurement of the actual pressing time, and measurement of the radial pressure acting upon the tool inner wall during the first pressing cycle or in each pressing cycle.
- 15. Method according to claim 4 or 9, characterized in that the pressure buildup and the pressure relief of the hysteresis curve are controlled by time control of the stamp pressure such that the ascending slopes of the pressure-buildup curve and the pressure relief curve are almost identical.
- 16. Method according to one of claims 1 to 15, characterized in that the energy consumption of the friction material mixture is measured by temperature measurement in the press mold, and the temperature measuring signal controls the press temperature as a manipulated variable.
- 17. Method according to one of claims 1 to 15, characterized in that the radiation heat of the friction lining ejected after the pressing process is measured, and the temperature measuring signal controls the press temperature as a manipulated variable.
- 18. Method according to one of claims 1 to 15, characterized in that the electrical heating capacity of the press is measured, and the measuring signal controls the press temperature as a manipulated variable.
- 19. Method according to one of claims 1 to 18, characterized in that the compressibility, the density, the moduli of elasticity in the three space coordinates, the dimensions of the friction lining or a combination of the aforementioned (lining properties) are used as controlled variable.
- 20. Application of the method according to one of claims 1 to 19 as a method for testing friction lining mixtures.

#### Abstract

## Method for manufacturing friction linings

In a method for manufacturing friction linings with or without an intermediate layer by compressing the friction material mixtures in a mold of a press during a pressing process comprising at least one pressing cycle, wherein a press control unit controls a plurality of manipulated variables individually or in combination with each other to attain a given lining property (controlled variable) of the friction linings, it is provided that at least one characteristic value representative of the lining property of the friction linings is measured in a first pressing cycle or in a plurality of pressing cycles, and that the manipulated variables are controlled in dependence on the at least one measured characteristic value of the current pressing cycle, the subsequent pressing cycles and/or the subsequent pressing processes.

(Fig. 1)

-1/4-




FIG.1

-2/4-




FIG.2






FIG.4



F/G.3



F1G.5

	· 3
	PLEASE NOTE:
	YOU MUST
	COMPLETE THE
_	FOLLOWING:

### Insert Title

Check Box If Appropriate — For Use Without Specification

# COMBINED DECLARATION AND POWER OF ATTORNEY

<b>ATTORNEY</b>	DOCKET	NO

F		DESIGN APPLI		ALIORNE	DOCKETT	10.
invent below	As a below named inventor, I hereby declare that: my residence post office address and citizenship are as stated next to my name; that I verily believe that I am the original, first and sole inventor (if only one inventor is named below) or a joint inventor (if plural inventors are named below) of the subject matter which is claimed and for which a patent is sought on the invention entitled: *  Method for manufacturing friction linings					
			CT TC CTON TT	iiiigs		
	The Specification v Serial No was filed as PCT in	attached hereto unless was filed on and was amended nternational application no and was amended under	on	and was	assigned	ed:
I specifi	I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.					
I a	acknowledge the duty to of Federal Regulations	o disclose information m s, §1.56.	aterial to patent	ability as d	efined in T	itle 37,
I do not know and do not believe the same was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof, or more than one year prior to this application, that the same was not in public use or on sale in the United States of America more than one year prior to this application, that the invention has not been patented or made the subject of an inventor's certificate issued before the date of this application in any country foreign to the United States of America on an application filed by me or my legal representatives or assigns more than twelve months (six months for designs) prior to this application, and that no application for patent or inventor's certificate on this invention has been filed in any country foreign to the United States of America prior to this application by me or my legal representatives or assigns, except as follows:  I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below:						
		nventor's certificate liste	ed below:			
	oreign Application(s)	_			Priority	Claimed
199	29 698.7	Germany	June 29,	1999	×	

(if appropriate)

0 11			Titority	Ciamico	
199 29 698.7	Germany	June 29, 1999	57		
(Number)	(Country)	(Month/Day/Year Filed)	<b>⊠</b> Yes	□ No	
(Number)	(Country)	(Month/Day/Year Filed)	□ Yes	□ No	
(Number)	(Country)	(Month/Day/Year Filed)	☐ Yes	□ No	
(Number)	(Country)	(Month/Day/Year Filed)	☐ Yes	□ No	
(Number)	(Country)	(Month/Day/Year Filed)	□ Yes	□ No	
All Foreign Applications, Months (6 Months for De	if any, for any Patent signs) Prior To The Fi	or Inventor's Certificate File ling Date of This Application	d More T	han 12	
Country	Application		Date of Filing (Month/Day/Year)		
T1. 1 1 1 1 1					
i nereny claim the be	netit linger Litle 35 - L	Inited States Code \$120 of	ansı IInite	d State	

benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

(Application Serial No.)	(Filing Date)	(Status — patented, pending, abandoned)
(Application Serial No.)	(Filing Date)	(Status — patented, pending, abandoned

I hereby appoint the following attorneys to prosecute this application and/or an international application based on this application and to transact all business in the Patent and Trademark Office connected therewith and in connection with the resulting patent based on instructions received from the entity who first sent the application papers to the attorneys identified below, unless the inventor(s) or assignee provides said attorneys with a written notice to the contrary:

Vincent L. Ramik - Registration No. 20,663

PLEASE NOTE: YOU MUST COMPLETE THE FOLLOWING:

Send Correspondence to: DILLER, RAMIK & WIGHT, P.C.

**Merrion Square Suite 101** 

7345 McWhorter Place

Annandale, Virginia 22003 Telephone (703) 642-5705

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued

thereon. GIVEN NAME FAMILY NAME INVENTOR'S SIGNATURE Fun Name of First or Sole Inventor: Intert Name of Inventor Trisert Date This Bocument Is Signed 62.02 Wolfgang Hogenkamp Insert Residence RESIDENCE (City, State & Country) CITIZENSHIP 42855 <u>Remschei</u>d, Germany German POST OFFICE ADDRESS (Complete Street Address including City State & Country) Insert Post Office Address Rather Strasse 51, 42855 Remscheid. Germany u GIVEN NAME FAMILY NAME INVENTOR'S SIGNATURE DATE Full Name of Second 15.4.02 Ernst Pollmann www RESIDENCE (City, State & Country) CITIZENSHIP N 51377 Leverkusen, Germany German POST OFFICE ADDRESS (Complete Street Address including City State & Country) Charlottenburger Strasse 26 c, 51377 Leverkusen, Germany Full Name of Third Inventor, if any: GIVEN NAME **FAMILY NAME** INVENTOR'S SIGNATURE DATE see above RESIDENCE (City, State & Country) CITIZENSHIP POST OFFICE ADDRESS (Complete Street Address including City, State & Country) GIVEN NAME INVENTOR'S SIGNATURE Full Name of Fourth Inventor, if any: **FAMILY NAME** DATE see above RESIDENCE (City State & Country) CITIZENSHIP POST OFFICE ADDRESS (Complete Street Address including City State & Country) Full Name of Fifth Inventor, if any: GIVEN NAME INVENTOR'S SIGNATURE DATE FAMILY NAME RESIDENCE (City, State & Country) CITIZENSHIP \*Note: Must be completed date this document is POST OFFICE ADDRESS (Complete Street Address including City, State & Country) signed. Page 2 of 2